

A¹

(c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative.

Please amend claim 11 as follows:

A²

(11) A curable blend according to Claim 1 wherein the reactive component is selected from the group consisting of: an aliphatic monofunctional acrylate, an aliphatic multifunctional acrylate, an aliphatic monofunctional methacrylate, or an aliphatic multifunctional methacrylate.

Please amend claim 13 as follows:

A³

(13) A curable blend according to Claim 1 wherein the reactive component is selected from the group consisting of: a polyoxyalkylene monofunctional acrylate, a polyoxyalkylene multifunctional acrylate, a polyoxyalkylene monofunctional methacrylate, or a polyoxyalkylene multifunctional methacrylate.

Please amend claim 25 as follows:

—

(25) A coated substrate wherein the coating comprises a crosslinked composition prepared from a homogeneous blend comprising:

A⁴

(a) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,

(b) more than 25% based on weight of a bis-phenol-A derivative that is end-capped with acrylate functionality, and

A⁴

(c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the bis-phenol-A derivative.

Please amend claim 39 as follows

- (39) A process for preparing a coated substrate comprising:
- (a) obtaining a substrate with a clean surface,
 - (b) applying a coating to the substrate wherein the coating comprises a homogeneous blend comprising:
 - (x) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,
 - (y) more than 25 percent based on weight of a bis-phenol-A derivative that is end-capped with acrylate functionality, and
 - (z) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the bis-phenol-A derivative, and
 - (c) curing the homogeneous blend by exposing said blend to a sufficient level of a predetermined form of radiant energy.

A⁵

[Please amend claim 40 as follows:]

- (40) A process for preparing a coated substrate according to Claim 39 wherein the radiant energy is derived from a source which is a member selected from the group consisting of

electron beam, ultraviolet, radiofrequency, infrared, and combinations thereof.

[Please amend claim 41 as follows:]

(41) A process for preparing a coated substrate according to Claim 40, wherein the substrate is an electrically conductive material that is heated in a radiofrequency induction field to initiate catalyst activity.

[Please amend claim 42 as follows:]

(42) A process for preparing a coated substrate comprising:

(a) obtaining a substrate with a clean surface,

AS (b) applying a coating to the substrate wherein the coating comprises a homogeneous blend comprising:

(w) a 1,2 – polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,

(x) more than 25 percent based on weight of a bis-phenol a derivative that is end-capped with acrylate functionality, and

(y) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2 – polybutadiene oligomer and the bis-phenol-A derivative, and

(z) a ground state catalyst that initiates free radical cross-linking upon exposure to heat, and

(c) curing the homogeneous blend by exposing said blend to a sufficient level of a predetermined form of thermal energy.

Please add the following new claims:

- (44) A curable homogeneous blend comprising:
- (a) a 1,2-polybutadiene copolymer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,
 - (b) a bis-phenol-A derivative that is end-capped with acrylate functionality, and
 - (c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative.
- (45) A curable blend according to Claim 44 wherein the 1,2-polybutadiene copolymer is prepared from butadiene and a vinyl monomer that is a member selected from the group consisting of: styrene, vinyl acetate, divinyl benzene, isoprene, chloroprene, alkyl acrylates, alkyl methacrylates, ethylene, propylene, butylene and mixtures thereof.

- (46) A curable homogeneous blend comprising:
- (a) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,
 - (b) an epoxy prepared from epichlorohydrin and bis-phenol-A that is end-capped with acrylate functionality, and
 - (c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative.

(47) A curable homogeneous blend comprising:

(a) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,

(b) a bis-phenol-A derivative that is end-capped with acrylate functionality,
and

(c) a reactive component substituted with long chain alkyl or alkoxy segments that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative.

(48) A curable blend according to Claim 47 wherein the substituted reactive component is a member selected from the group consisting of: alkoxyated nonyl phenol acrylate and alkoxyated nonyl phenol methacrylate.

(49) A curable homogeneous blend comprising:

(a) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,

(b) a bis-phenol-A derivative that is end-capped with acrylate functionality,
and

(c) a heterocyclic reactive organic compound that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative.

(50) A curable blend according to Claim 49 wherein the heterocyclic compound is a member selected from the group consisting of: n-vinyl pyrrolidone and methyl-n-vinyl pyrrolidone.

(51) A curable homogeneous blend comprising:

- (a) a 1,2-polybutadiene oligomer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,
- (b) a bis-phenol-A derivative that is end-capped with acrylate functionality,
- (c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the acrylated bis-phenol-A derivative, and
- (d) a hydroxy functional adhesion promoter.

(52) A curable blend according to Claim 50 wherein the hydroxy functional compound is a member selected from the group consisting of hydroxyethyl methacrylate and ethoxylated hydroxyethyl methacrylate.

(53) A coated substrate wherein the coating comprises a crosslinked composition prepared from a homogeneous blend comprising:

- (a) a 1,2-polybutadiene copolymer having a number average molecular weight (Mn) of about 500 Daltons to about 50,000 Daltons,
 - (b) a bis-phenol-A derivative that is end-capped with acrylate functionality,
- and

(c) a reactive component that has at least one terminal double bond and that enhances the compatibility between the 1,2-polybutadiene oligomer and the bis-phenol-A derivative.

Ab (54) A coated substrate according to Claim 52 wherein the 1,2-polybutadiene copolymer is prepared from butadiene and a vinyl monomer that is a member selected from the group consisting of: styrene, vinyl acetate, divinyl benzene, isoprene, chloroprene, alkyl acrylates, alkyl methacrylates, ethylene, propylene, butylene and mixtures thereof.

(55) A coated substrate according to Claim 52 wherein the bis-phenol-A derivative is prepared from epichlorohydrin and bis-phenol-A.
